



# TEST REPORT



ISSUED BY **British Board of Agrément**  
DATE OF ISSUE **21 August 2012**  
SERIAL NUMBER **50831THA**

REPORT PREPARED BY

**S Whitehead**  
Senior Test Technician

Bucknalls Lane, Garston  
Watford, Herts WD25 9BA  
Tel: 01923 665300  
Fax: 01923 665301  
e-mail: [testing@bba.star.co.uk](mailto:testing@bba.star.co.uk)  
<http://www.bbaocerts.co.uk>

©British Board of Agrément 2012

AUTHORISED BY

**J Holdsworth**  
Test Operations Manager

CLIENT: Boulder Developments Ltd.  
BHF  
Main Street  
Norwell  
Newark  
Nottinghamshire  
NG23 6JN

JOB No: T150831

## 1 INTRODUCTION

The test specimen was supplied by the client and described as Multifoil (890100175). It was delivered in the form of 760mm x760mm x 120mm loose layer Multifoil.

## 2 METHOD

Heat Flow Meter Method of ISO 8301 : 1991 and BS EN 12667 : 2001 using the BBA single specimen symmetric test facility designated K4. Edge guarding is provided by an independently heated zone at the perimeter of each plate and apparatus wall temperatures controlled to match the mean specimen temperature. Specimen thickness was measured in accordance with BS EN 823.

## 3 SPECIMEN PREPARATION

The test specimen was assigned the BBA designation number T150831/1 and stored in a well-ventilated position in an air-conditioned room at  $23 \pm 2^\circ\text{C}$ ,  $50 \pm 5\%$  rh until it was tested.

## 4 MEASURED PROPERTIES

Thermal resistance per layer $\text{m}^2\text{-KW}$	Density $\text{kg/m}^3$	Mean temperature ( $^\circ\text{C}$ )
$3.46 \pm 2.5\%$	14.6	9.8

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor  $k=2$ , providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025:2005.

This report provides traceability of measurement to recognised national standards, and to the units of measurement realised at the National Physical Laboratory or other recognised national standards laboratories. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

# TEST REPORT

UKAS ACCREDITED TESTING LABORATORY No 0357

SERIAL NUMBER 50831THA

## 8 ADDITIONAL INFORMATION (not covered by UKAS Test Schedule)

The emissivity of the foil itself has not been measured. The client stated the emissivity value for the foil as 0.05. The thermal resistance value (based on this emissivity value) for the airspaces and product + airspaces, calculated to annex B.2 (Unventilated airspaces with length and width both more than 10 times thickness) of BS EN ISO 6946 : 2007 - are given in the table below.

Emissivity, $\epsilon$	Thermal resistance (horizontal heat flow – up to 30° from horizontal plane) ( $m^2 \cdot K/W$ ) <sup>[1][3]</sup>		Thermal resistance (vertical heat flow – up to 30° from horizontal plane) ( $m^2 \cdot K/W$ ) <sup>[1][3]</sup>	
	20mm and greater Airspace	≥20mm Airspace + specimen <sup>[2]</sup> + ≥20mm Airspace	13mm and greater Airspace	≥13mm Airspace + specimen <sup>[2]</sup> + ≥13mm Airspace
0.05	0.71	4.88	0.48	4.42

[1] Assuming: mean cavity temperature,  $T_m=10^\circ C$ ; temperature drop across the cavity,  $\Delta T=5K$ ; and alternate face of airspace has emissivity,  $\epsilon=0.90$

[2] Assuming: Thermal resistance of specimen is ... $m^2 K/W$  as given above

[3] These R values are for illustrative purposes only and have been calculated using the client emissivity values. Therefore they should not be used as design values