

# Product Data Sheet

## Gyproc® Moisture Resistant 12.5mm


Gyproc Moisture Resistant 12.5mm is a plasterboard with water repellent additives in the core.

### Where to use

Use it in intermittent moisture applications such as kitchens, bathrooms and sheltered external soffits.

### Certifications

Environmental Product Declaration (EPD) available [Click here](#).



## Product information

### Composition

The plasterboard is made of a gypsum core between paper liners. It has water repellent additives in its core.

### Colour

Face colour: Green.  
Reverse colour: Green.

### DIMENSIONS AND WEIGHTS

PRODUCT SIZES (mm)	1200 X 2400	1200 X 2700	1200 X 3000
Nominal thickness (mm)	12.5	12.5	12.5
Minimum weight (kg/m <sup>2</sup> )	8.3	8.3	8.3
Edge options	Tapered edge, Square edge	Tapered edge only	Tapered edge only
Number of tapered edges	2	2	2
Width: maximum tolerance (mm)	+0	+0	+0
Width: minimum tolerance (mm)	-4	-4	-4
Length: maximum tolerance (mm)	+0	+0	+0
Length: minimum tolerance (mm)	-5	-5	-5
Taper: maximum width (mm)	80	80	80
Taper: minimum width (mm)	40	40	40
Taper: maximum depth (mm)	2.5	2.5	2.5
Taper: minimum depth (mm)	0.6	0.6	0.6
Squareness: 1200mm width boards (maximum difference in diagonal measurements, mm)	5	5	5

NB: Dimensional tolerances. Quality controls are set to meet customer requirements between these maximum and minimum tolerances.

# Product Data Sheet

## Gyproc® Moisture Resistant 12.5mm

### Performance

Here we only provide performance information related to the product. Please see the White Book for system-dependent performance.

### Standards

EN 520:2004+A1:2009, Type H1.

Declarations of Performance (DoP) available [Click here](#).

Reaction to fire	A2-s1, d0
Thermal conductivity (W/mK)	0.19
Moisture resistance	H1
Water vapour permeability ( $\mu$ )	10
Water resistance (maximum total water absorption when tested to EN520 clause 5.9.2, %)	5
Maximum continuous temperature exposure ( $^{\circ}$ C)	49

### Installation

#### Effect of condensation

The thermal insulation and ventilation requirements of national Building Regulations aim to reduce the risk of condensation and mould growth in new buildings. However, designers should take care to eliminate all possibility of problems caused by condensation, particularly in refurbishment projects.

#### Cutting

Either cut the board with a plasterboard saw, or score the front face paper with a sharp knife, snap it over a straightedge, then cut the back face paper. Cut holes for things like socket boxes using a utility saw.

#### Fixing

Fix the board with the decorative side facing outwards to receive finishes. Install fixings at least 13mm from cut edges and 10mm from bound edges. Position cut edges at internal angles wherever possible. Stagger horizontal and vertical joints between layers by at least 600mm.

#### Jointing

Finishing should start as soon as practicable after board fixing to limit the risk of damage or UV-degradation of the paper liner. Suitable for finishing with jointing systems complying with EN13963 including the Gyproc range.

#### Full-surface finishing

Moisture resistant boards should not normally be skim plastered. If the requirement for moisture performance was temporary (e.g. shell and core construction) and plastering is subsequently specified, pre-treatment with Thistle Bond-it is required.

#### Painting

Decoration should start as soon as practicable after the finishing system is dry. Jointing systems should be finished with Gyproc Drywall Primer before painting.

#### Wallpapering

Decoration should start as soon as practicable after the finishing system is dry. Jointing systems should be finished with Gyproc Drywall Sealer before application of wallcoverings.

#### Snagging and minor repairs

For minor damage and dents, check that the board core isn't shattered. If it's intact, fill the damaged area with Gyproc EasiFill 60, allow it to set, then apply a second coat if you need to. When it's dry, sand it to a finish before redecorating the area.

For a damaged core, broken edges or extensive damage, repair and replacement procedures differ depending on the number of board layers and fire resistance of the system; please contact our Technical Support Team for specific advice.

# Product Data Sheet

## Gyproc® Moisture Resistant 12.5mm

### Sitework

#### Storage

Keep boards dry, and make sure floor or ground surfaces are flat and strong enough to support them.

#### Safety Data Sheet

Safety Data Sheet (SDS) available. [Click here.](#)

#### Packaging overview

Supplied on a reusable wooden pallet.

### Environmental

#### Recyclability

You can recycle this product as long as it has minimal contamination from non-gypsum materials.

#### Disposal

Segregate boards from non-gypsum waste for recycling where possible. Dispose of them according to local authority requirements.

#### BES 6001 classification

Excellent.



"Gyproc", "Thistle", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover and "Artex" is a registered trademark of Saint-Gobain Construction Products UK Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: [british-gypsum.com](http://british-gypsum.com). For information about products supplied by Artex Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.